



Physical Property Data Summary

1568 Acetate Sheeting AA Faceshield Stock (Various Gauges)

<u>Property</u>	<u>0.001”-.030”</u>	<u>0.031”-0.060”</u>	<u>Test Method</u>
Tensile Strength (psi) (Minimum)	6000	5500	ASTM D 882
Elongation (%) (Minimum @ Break)	25.0	25.0	ASTM D 882
Light Transmission (%) (Minimum)	88.0	85.0	ASTM D 1003
Haze (%) (Maximum)	3.0	3.0	ASTM D 1003
Flammability (in ² /sec) Flammability (in/min)	0.25	0.25 3.50	ASTM D 568 ASTM D 635
Water Absorption (Maximum Gain %) (Maximum Loss %)	7.0 4.0	6.5 2.0	ASTM D 570

This information contained herein is furnished without warranty of any kind. Users should consider these data as only a supplement to other information gathered by them and make independent determinations of suitability and completeness of information from all sources to assure proper use.